NAVAL SHORE FACILITIES CORROSION CONTROL PROGRAM

DAVID F. JUTTON, E.I.T.

NATIONAL ASSOCIATION OF CORROSION ENGENEERS CATHODIC PROTECTION SPECIALIST

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

IMPACTS OF CORROSION

CORROSION IMPACTS SHORE FACILITIES IN MORE WAYS, AND TO A FAR GREATER DEGREE THAN REGULARLY CONSIDERED:

- COSTLY SYSTEM REPAIRS & REPLACEMENTS
- DOWNTIME AND DISRUPTION OF SERVICE
- EXPENSIVE LOSS OF PRODUCT
- ENVIRONMENTAL AND SAFETY HAZARDS
- DECREASED SYSTEM CAPACITIES
- ADVERSE IMPACTS ON OPERATIONAL READINESS

WHY IS CORROSION A BIG PROBLEM?

- CORROSION IS A FORCE OF NATURE THAT WILL OCCUR. WHEN LEFT UNCHECKED, IT IS NOT A MATTER OF IF A STRUCTURE WILL CORRODE, BUT WHEN IT WILL FAIL
- MANY CRITICAL FACILITIES ARE BURIED OR SUBMERGED - "OUT OF SIGHT, OUT OF MIND".
 CORROSION PROBLEMS ARE NORMALLY IDENTIFIED AFTER FAILURE WHEN IT BECOMES COSTLY TO FIX

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

TIME TO CORROSION FAILURE

NEW OR NEWLY REPAIRED STEEL STRUCTURES CAN FAIL OR REQUIRE MAJOR REPAIRS WITHIN THE FOLLOWING TIME FRAMES:

- BURIED STEEL STRUCTURES: 6 YEARS (CORROSION CAUSED HOLES)
- SUBMERGED STEEL WATERFRONT STRUCTURES: 9 YEARS (SIGNIFICANT THINNING OF METAL TO ADVERSELY AFFECT STRUCTURAL CAPACITY)

CORROSION CONTROL METHODS

- PROPERLY APPLIED PROTECTIVE COATINGS ARE EFFECTIVE FOR STRUCTURES EXPOSED TO THE ATMOSPHERE. FOR BURIED OR SUBMERGED STRUCTURES, CONCENTRATED CORROSION WILL OCCUR AT DEFECTS IN THE COATINGS
- CATHODIC PROTECTION (CP), A VERY EFFECTIVE CORROSION CONTROL METHOD ON ITS OWN, COMPLEMENTS COATINGS AND WILL EXTEND COATING AND STRUCTURE LIFE SIGNIFICANTLY

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

<u>CP AND CORROSION CONTROL</u> BENEFITS

- A PROPERLY OPERATED AND MAINTAINED CP SYSTEM CAN EXTEND THE LIFE OF A STRUCTURE AT LEAST 15 - 20 YEARS
- REPLACEMENT OF CP COMPONENTS EVERY 15 TO 20 YEARS CAN EXTEND STRUCTURE LIFE INDEFINITELY
- THE ANNUAL MAINTENANCE AND PERIODIC REPAIR COSTS ARE FAR LESS THAN MAJOR REPAIRS TO OR REPLACEMENT OF THE STRUCTURES THEMSELVES
- AVOID HIGH ENVIRONMENTAL CLEANUP COSTS

CP SYSTEM LIMITATIONS

- CAN ONLY PROTECT STRUCTURES THAT ARE BURIED OR SUBMERGED. COATINGS AND MATERIAL SELECTION ARE NECESSARY FOR ATMOSPHERIC CORROSION CONTROL
- CANNOT REPLACE METAL ALREADY LOST
- IMPRESSED CURRENT CP SYSTEMS CAN INADVERTENTLY CAUSE CORROSION ON NEIGHBORING STRUCTURES IF NOT PROPERLY DESIGNED

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

CORROSION CONTROL REQUIRED

CORROSION CONTROL IN CONJUCTION WITH OTHER PROTECTIVE MEASURES IS REQUIRED FOR THE FOLLOWING BURIED OR SUBMEREGED METTALIC UTILITY SYSTEMS:

- NATURAL GAS PIPELINES
- OXYGEN PIPELINES
- PETROLEUM, OIL & LUBICANTS (POL) PIPELINES
- POL AND FUEL STORAGE TANKS
- HAZARDOUS SUBSTANCE STORAGE TANKS
- WATER STORAGE TANK INTERIORS

CORROSION CONTROL RECOMMENDED

CORROSION CONTROL IS RECOMMENDED FOR THE FOLLOWING BURIED OR SUBMEREGED METTALIC UTILITY SYSTEMS:

- STEAM DISTRIBUTION SYSTEMS
- COMPRESSED AIR DISTRIBUTION SYSTEMS
- STEEL SHEET BULKHEADS
- STEEL FENDER AND BEARING PILES FOR PIERS
- MOORING COMPONENTS

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

LANTDIV'S CORROSION CONTROL SERVICES

- PROVIDE ASSISTANCE TO IMPLEMENT A CORROSION CONTROL PROGRAM PER LANTNAVFACENGCOM INSTRUCTION 11014.9 OF 21 MAR 95.
- REVIEW CONSTRUCTION AND MAINTENANCE PROJECTS FOR APPROPRIATE CORROSION CONTROL MEASURES
- PREPARE AND REVIEW PROJECTS FOR CORRECTING CORROSION PROBLEMS
- PROVIDE TECHNICAL ASSISTANCE DURING THE INSTALLATION OR APPLICATION OF COOROSION CONTROL MEASURES.

(corrosion control services cont.)

- IMPLEMENT CORROSION CONTROL MAINTENANCE AND OPERATION PLANS TO KEEP CORROSION CONTROL SYSTEMS EFFECTIVE.
- MONITOR OPERATION OF EXISTING CATHODIC PROTECTION SYSTEMS (MONTHLY & ANNUAL INSPECTIONS)
- PROVIDE TRAINING IN CORROSION CONTROL
- TEST AND ADJUST CATHODIC PROTECTION SYSTEMS
- PROVIDE DETAILED CORROSION SURVEYS

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

CORROSION SURVEYS

IAW NAVFAC INSTRUCTION 11014.52, PERIODIC FIELD SURVEYS (EVERY THREE TO FIVE YEARS) ARE NECESSARY TO:

- ASSESS EXISTING CONDITION OF THE STRUCTURES
- ASSESS CATHODIC PROTECTION SYSTEM EFFECTIVENESS
- ADJUST CATHODIC PROTECTION SYSTEMS TO PROVIDE CONTINUED PROTECTION

(corrosion surveys cont.)

- SEARCH FOR UNPROTECTED STRUCTURES WHERE CORROSION CONTROL SYSTEMS WOULD BE BENEFICIAL OR ARE MANDATED
- RECOMMEND REPAIRS AND UPGRADES TO EXISTING CORROSION CONTROL SYSTEMS
- PROVIDE TECHNICAL ASSISTANCE SUCH AS PREPARING CORROSION CONTROL PROJECT DOCUMENTS AND DESIGNS

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

CORROSION PROGRAM GOALS

THIS!!



SUBMERGED STEEL PILE AFTER 12 YEARS. COATING IN GOOD CONDITION - LITTLE OR NO CORROSION



PIPELINES BEING INSTALLED WITH EPOXY COATING AND CP SYSTEM

CORROSION PROGRAM GOALS

NOT THIS:





PILE OF CORRODED PIPE

SHEET PILE WITH NUMEROUS LARGE CORROSION HOLES

ATLANTIC DIVISION NAVAL FACILITIES ENGINEERING COMMAND

CORROSION CONTROL PROGRAM POINT OF CONTACT

David Jutton, Corrosion Control Program Coordinator LANTNAVFACENGCOM 1510 Gilbert Street, Code 1614C Norfolk, VA 23511

DSN: 262-4650 COMM'L: (757) 322-4650

FAX: (757) 322-4715

EMAIL: juttondf@efdlant.navfac.navy.mil